

S1 1 PN="JP 50075256"

1/5/1 (Item 1 from file: 351)
DIALOG(R)File 351:DERWENT WPI
(c)1999 Derwent Info Ltd. All rts. reserv.

001647286

WPI Acc No: 76-81734X/197644

Polyolefin polyamide laminate container - having polyethylene,
ethylene-zinc meth-acrylate copolymer inner layer, nylon outer layer

Patent Assignee: TORAY IND INC (TORA)

Number of Countries: 001 Number of Patents: 001

Patent Family:

Patent No	Kind	Date	Applicat No	Kind	Date	Main IPC	Week
JP 50075256	A	19750620					197644 B

Priority Applications (No Type Date): JP 73123971 A 19731106

Abstract (Basic): JP 50075256 A

Polyolefins (melt index 0.05-1) and/or polyamides (relative viscosity 2-6) which contained 3-45% modified ethylene polymers contng. 0.1-10 mole % unsatd. carboxylic acids or their derivs. as comonomers were used to prep. containers having polyamide layer-polyolefin layer ratio 0.01-0.3 by blow moulding. In an example, a container having good adhesion between layers was prepd. by using a blent of 85% high-d. polyethylene and 15% ethylene-zinc methacrylate copolymer as an inner layer and nylon 6 as an outer layer.

Title Terms: POLYOLEFIN; POLYAMIDE; LAMINATE; CONTAINER; POLYETHYLENE;
ETHYLENE; ZINC; METHO; ACRYLATE; COPOLYMER; INNER; LAYER; NYLON; OUTER;
LAYER

Derwent Class: A17; A23; A92; Q32

International Patent Class (Additional): B29D-000/00; B65D-000/00

File Segment: CPI; EngPI